

18. A process according to claim 11 wherein the oxidation catalyst is obtained by heating a composition containing oxides of cobalt and of at least one element A selected from the group consisting of rare earths and yttrium, to a temperature in the range 900-1200°C.

B,
cont

19. A process according to claim 11 wherein the oxidation catalyst comprises a primary support in the form of a mesh, gauze, pad, or monolith formed from a high temperature iron/aluminium alloy or a mesh, gauze, pad, monolith, or foam of a ceramic material, a secondary support in the form of an alkali-free alumina or lanthana wash coat on said primary support; and, supported on said secondary support, an active coating of oxides of (a) at least one element A selected from the group consisting of rare earths and yttrium, and (b) cobalt, said cobalt and element A being in such proportions that the element A to cobalt atomic ratio is in the range 0.8 to 1.2, at least some of said cobalt and element A oxides being present as a mixed oxide phase with less than 30% of the cobalt (by atoms) being present as free cobalt oxides.

REMARKS

The Preliminary Amendment accompanies the filing of a Continuation Application under 35 U.S.C. Section 120 of PCT/GB97/03193 which designated the US.

Favorable consideration and an early action on the merits of the added claims are respectfully solicited.

Respectfully submitted,

June 17, 1999
Dated

John F. Daniels
John F. Daniels, III
Reg. No. 34,314
Attorney for Applicants
302/887-3727